

Avery Dennison® DOL 6060 Anti Graffiti

Gloss Clear Polyester Overlaminating Film

Features

- High gloss finish
- Aids in application of printed graphic
- Enhances colours and depth of image
- Excellent UV, temperature, humidity and salt spray resistance
- Improves image durability up to 4 years
- Good abrasion resistance
- Anti Graffiti - protects graphic from vandalism

Description



Film: 25 micron gloss clear Polyester



Adhesive: Clear Permanent acrylic



Backing: Bleached Kraft paper



Outdoor life: Up to 3 years

Conversion*

- | | |
|--|--|
| <input checked="" type="checkbox"/> Flat bed cutters | <input checked="" type="checkbox"/> Cold overlaminate |
| <input checked="" type="checkbox"/> Friction fed cutters | <input type="checkbox"/> E-ink printing |
| <input type="checkbox"/> Die cutting | <input type="checkbox"/> Water based inkjet |
| <input type="checkbox"/> Thermal transfer | <input type="checkbox"/> Solvent inkjet |
| <input type="checkbox"/> Screen printing | <input type="checkbox"/> UV Cured inkjet |

*Always test with your combination of printer and inks prior to commercial use.

Common Applications

- Backlit signs
- Interior & exterior signs
- Wall murals

Uses

Avery Dennison® DOL 6060 Anti-Graffiti is a clear polyester overlaminating film designed to protect indoor and outdoor markings and decorations against permanent damage from chemicals, solvents or graffiti paints. DOL 6060 Anti-Graffiti overlaminate can be used over screen and digital graphics to protect the graphic against chemical or mechanical attack

Note

PVC / Polyester film combinations are not compatible with acrylic, polycarbonate and other substrates that have a tendency to outgas. Application to these substrates should be avoided as bubbling or blistering can occur due to the inability of Polyester to allow transmission of gas generated by these substrates.

Physical characteristics

General

Caliper, facefilm	ISO 534	25 micron
Caliper, facefilm & adhesive	ISO 534	50 micron
Dimensional stability	DIN 38464	0.1mm max
Gloss	Hunter Gloss @ 60	90%
Adhesion, initial	Finat FTM- 1, stainless steel	500 N/m
Adhesion, ultimate	Finat FTM-1, stainless steel	600 N/m
Flammability		Self extinguishing
Shelf life	Stored at 22° C/50-55 % RH	2 years
Expected Durability**	Vertical exposure	Up to 3 years

Thermal

Lamination temperature	See relevant technical bulletins
Service temperature range	- 40°C to + 80°C

Chemical

Resistant to most petroleum based oils, greases, and aliphatic solvents

Resistant to mild acids, alkalis and salts

Prolonged immersion in gasoline and similar fluids is not recommended.

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications.

They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warranty

Avery Dennison® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery Dennison® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Expected Durability

The expected durability of Avery Dennison films are defined as the expected performance life of the Avery Dennison graphic film(s) within Zone 1 of the Avery Dennison zone system, in outdoor vertical exposure conditions.

The actual performance life will depend on a variety of factors, including selection and preparation of substrate, angle and direction of exposure, application methods, environmental conditions and cleaning/maintenance of the films. In case of films used in areas of high temperatures or humidity, high altitudes and industrially polluted areas the performance will be further reduced.

Expected Durability and Warranted Period Definitions

Expected durability is the expected period of time defined in the product data sheet, the product should, but is not warranted to, perform satisfactorily when applied in vertical exposure conditions as defined in Instructional Bulletin 1.30. The warranted period as defined in the appropriate ICS Performance Guarantee Bulletin, is the maximum period of time Avery Dennison will warrant the finished products performance in accordance with ICS Performance Guarantee Terms and Conditions 1.0, provided that the film is properly stored, converted and installed in accordance with Avery Dennison guidelines.

Test Methods

Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) or ASTM 1000 is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion.