



DR Grey 20 XTRM

Optical & Solar Properties

	Single Pane	Double Pane
Visible Light Transmitted	20%	18%
Visible Light Reflected (interior)	17%	23%
Visible Light Reflected (exterior)	40%	41%
Ultra Violet Block	99.9%	99.9%
Total Solar Energy Reflected	44%	44%
Total Solar Energy Transmitted	17%	15%
Total Solar Energy Absorbed	39%	41%
Emissivity (Room Side)	0.84	0.84
Glare Reduction	78%	78%
Selective InfraRed Reduction (SIRR)	83%	83%
InfraRed Energy Rejection (IRER)	73%	73%
Shading Coefficient	0.33	0.25
Solar Heat Gain Coeff. (G-Value)	0.29	0.22
U-Value Winter (IP)	1.04	0.48
U-Value Winter (SI)	5.91	2.73
Luminous Efficacy	0.60	0.72
Total Solar Energy Rejected	71%	78%

R122W6X - Pressure Sensitive Adhesive



Powered by
NanoTechnology

