



DS Print SR 4 mil i

Optical & Solar Properties

	Single Pane
Visible Light Transmitted	89%
Visible Light Reflected (interior)	11%
Visible Light Reflected (exterior)	11%
Ultra Violet Block	90%
Total Solar Energy Reflected	10%
Total Solar Energy Transmitted	81%
Total Solar Energy Absorbed	9%
Emissivity (Room Side)	0.82
Glare Reduction	1%
Selective InfraRed Reduction (SIRR)	
InfraRed Energy Rejection (IRER)	
Shading Coefficient	0.97
Solar Heat Gain Coeff. (G-Value)	0.84
U-Value Winter (IP)	1.03
U-Value Winter (SI)	5.85
Luminous Efficacy	0.92
Total Solar Energy Rejected	16%

R12325SR - Pressure Sensitive Adhesive